




# TANFILM DIP RESISTOR NETWORKS



- MIL qualified to both MIL-R-83401/01 and MIL-R-83401/02
- MIL spec qualified to .1% Tol, .02% available
- MIL spec qualified to 50 ppm/°C, 25 ppm/°C available
- Superior TCR tracking to 2 ppm/°C
- Ratios available to 0.01%
- Special mechanical and electrical configurations

TanFilm resistor networks are designed for use in applications requiring a high degree of reliability, stability, tight tolerance, close TCR tracking, and low noise. Our continuous feed, high vacuum sputtering process insures uniform properties from network to network. Precise state-of-the-art laser trimming enables us to easily zero in

the tightest ratios. Gold-plated copper leads are thermal pulse bonded to large-area gold conductor pads on the ceramic substrate assuring the most reliable termination and long-term stability. Passivated Tantalum Nitride resistor material offers performance far superior to military specifications and excellent environmental protection.

The versatile nature of our photo-etch process makes it readily adaptable to meet special customer requirements. Custom circuit designs and special mechanical configurations can be easily achieved with a modest set up charge. Full military screening is also available with all units.

## SPECIFICATIONS:

MIL Qualified Resistance Values:  
 Schematic A: 100Ω to 100KΩ  
 Schematic B: 100Ω to 70KΩ  
 Higher and lower resistance values available  
 Std Resistance Tolerances:  
 .1%, .25%, .5%, 1%, 2%, .02% available  
 Temperature Coefficient of Resistance:  
 ±25 ppm/°C, ±50 ppm/°C, ±100 ppm/°C, ±300 ppm/°C

TCR Tracking: 5 ppm/°C, except Models 1987 & 1998 below 500Ω (20 ppm/°C); 2 ppm/°C  
 Temperature Range: -55°C to +150°C  
 Power Rating @ 70°C:


Model	Wattage	
	Resistor	Network
1987	.1	1.3
1998	.1	1.5
1989	.2	1.4
1999	.2	1.6

Noise: Less than -30 dB  
 Lead Material: Gold plated copper  
 Substrate Material: 99.5% pure alumina ceramic  
 Construction: Ceramic sandwich epoxy encapsulant


Custom Circuit and Special Testing Available

Contact factory for any special features required


## STANDARD CIRCUITS:




Schematic B



Schematic B



Schematic A




Schematic A



**TANFILM DIP PERFORMANCE DATA:**

Test Per MIL-R-83401	MIL-R-83401 Limits (ΔR%)			TanFilm Test Data (ΔR%)	
	M	K	F	Maximum	Typical
Thermal Shock and Power Conditioning	0.70	.70	.50	.10	.02
Low Temperature Operation	0.50	.25	.10	.10	.02
Short Time Overload	0.50	.25	.10	.05	.02
Terminal Strength	0.25	.25	.25	.10	.02
Resistance to Soldering Heat	0.25	.25	.10	.10	.02
Moisture Resistance	0.50	.50	.40	.10	.02
Shock	0.25	.25	.25	.10	.02
Vibration	0.25	.25	.25	.10	.02
Life	2.00	.50	.50	.10	.02
High Temperature Exposure	1.00	.50	.20	.10	.02
Low Temperature Storage	0.50	.25	.10	.10	.02
25°C Double Load	2.00	.50	.50	.05	.02

**DIMENSIONS - INCHES:**



**HOW TO ORDER**

Sample Part No.

Model  
1999

Characteristic  
06

Resistance  
1001

Absolute Tolerance Code  
B

Ratio Tolerance to R<sub>1</sub>  
(if specified)

1989 7-resistor 14 Pin DIP, straight thru (MIL-R-83401-01, schematic A)

1999 8-resistor 16 Pin DIP, straight thru (MIL-R-83401-02, schematic A)

1987 13-resistor, 14 Pin DIP, one common lead (MIL-R-83401-01, schematic B)

1998 15-resistor, 16 Pin DIP, one common lead (MIL-R-83401-02, schematic B)

**Characteristic**

Code	Classification	TCR (ppm/°C)
01	Commercial Grade	± 100
02	Commercial Grade	± 50
03	Commercial Grade	± 25
04	Military Screening	± 300
05	Military Screening	± 100
06	Military Screening	± 50
07	Military Screening	± 25

**Resistance**

Standard MIL resistance code  
Example:  
1001 = 1000Ω

**Absolute/Ratio Tolerance Code**

Standard MIL tolerance code  
A ±.05%  
B ±.1%  
C ±.25%  
D ±.50%  
F ±1.0%  
G ±2.0%  
T ±.01%  
Q ±.02%