Amorphous Silicon Solar Cells Speccification


アモルファスシリコン太陽電池 仕様

 $M\ o\ d\ e\ I\ :\ A\ M\ -\ 5\ 6\ 1\ 3\ C\ -\ T$

1. Outside dimensions 外形寸法

Light Receiving Side (受光面)

Overcoat Side (オーハ゛ーコート面)



(dimension:mm)

Substrate Thickness (ガラス基板厚):1.6mm±0.2

Module Thickness (モジュール厚): 2,0mmMAX

Accepts normal soldering for bending

(一般の半田を使用してリート゛線付けが可能です。)

2. Rated Specifications (at 25%)

	I t e m	Specifications (Initial)
2.1	Open circuit voltage:Voc 開放電圧	Typical 5.1V at 50kLx SS
2.2	Short circuit Current: Isc 短絡電流	Typical 15.6mA at 50kLx SS
2.3	Operating Voltage & Operating Current:Vope-Iope 動作特性	Minimum 3.0V — 11.0mA at 50kLx SS
		Typical 3.3V - 14.5mA at 50kLx SS
		Typical 3.3V - 31.6mA at AM-1.5 100mW/cm ²
2.4	Maximum output:Pmax & optimum operating Volt:Vop opeimum operating Current:Iop 最大出力	Vop=3,9V (reference) 52mW Iop=13.3mA at 50kLx SS
		Vop=3.9V (reference) 1 1 0 mW I op=28.2 mA at AM-1.5 100 mW/cm²
2.5	Working temperature range:Topr 動作温度範囲	-10 to 60 ℃
2.6	Storage temperature range:Tstg 保存温度範囲	-20 to 70 ℃


アモルファスシリコン太陽電池 仕様


$M \ o \ d \ e \ I \ : \ A \ M - 5 \ 6 \ 1 \ 3 \ C \ A \ R - T$

1. Outside dimensions 外形寸法

Light Receiving Side (受光面)

Overcoat Side (オーハ゛ーコート面)





(dimension:mm)

Lead Wire	s : AWG28
a : 100	b:100

Not

Glass Substrate Thickness (ガラス基板厚):1.6mm±0.2

Module Thickness (モジュール厚) : 2,0mmMAX

Wire-Overcoat Thickness:3.1mmMAX (including Module) (リード線補正コート厚)

2. Rated Specifications (at 25%)

	I t e m	Specifications (Initial)
2.1	Open circuit voltage:Voc 開放電圧	Typical 5.1V at 50kLx SS
2.2	Short circuit Current: Isc 短絡電流	Typical 15.6mA at 50kLx SS
2.3	Operating Voltage & Operating Current:Vope-Iope 動作特性	Minimum 3.0V - 11.0mA at 50kLx SS
		Typical 3.3V - 14.5mA at 50kLx SS
		Typical 3.3V - 31.6mA at AM-1.5 100mW/cm ²
2.4	Maximum output:Pmax & optimum operating Volt:Vop opeimum operating Current:Iop 最大出力	Vop=3.9V (reference) 52mW Iop=13.3mA at 50kLx SS
		Vop=3.9V (reference) 1 1 0 mW Iop=28.2 mA at AM-1.5 100 mW/cm²
2.5	Working temperature range:Topr 動作温度範囲	-10 to 60℃
2.6	Storage temperature range: Tstg 保存温度範囲	-20 to 70℃


I - V Characteristics

REFERENCE

1.Model: AM-5613

2.Outside Dimension: 60.1mm × 36.7mm

SS:Solar Simulator



*このデータは標準的な出力特性を示すものであり、特性を保証するものではありません。

*The data are meant to show standard electric characteristics only , not intended to guarantee the characteristics.

Panasonic Solar Amorton Co.,Ltd.


出力の照度依存特性


REFERENCE

Dependence of Output on Illumination

1.Model: AM-5613

2.Outside Dimension: 60.1mm × 36.7mm





*このデータは標準的な出力特性を示すものであり、特性を保証するものではありません。

*The data are meant to show standard electric characteristics only , not intended to guarantee the characteristics.

Panasonic Solar Amorton Co., Ltd.


出力の温度依存特性


REFERENCE

Dependence of Output on Temperature

1.Model: AM-5613

2.Outside Dimension: 60.1mm × 36.7mm





*このデータは標準的な出力特性を示すものであり、特性を保証するものではありません。

*The data are meant to show standard electric characteristics only , not intended to guarantee the characteristics.

Panasonic Solar Amorton Co.,Ltd.