


PROCESS DETAILS

Process	Glass Passivated Mesa
Die Size	130 x 130 MILS
Die Thickness	8.7 MILS
Cathode Bonding Pad Area	99 x 49 MILS
Gate Bonding Pad Area	42 x 42 MILS
Top Side Metalization	Al - 45,000Å
Back Side Metalization	Al/Mo/Ni/Ag - 32,000Å

www.DataSheet4U.com

GEOMETRY



GROSS DIER PER 4 INCH WAFER

624

PRINCIPAL DEVICE TYPES

CS220-16M Series
CSDD-16M Series

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R0 (4- January 2006)