Primary lithium batteries G 26

3.0 V Primary lithium-sulfur dioxide (Li-SO₂) High drain capability D-size spiral cell



Benefits

- High and stable discharge voltage
- High pulse capability
- Performance not affected by cell orientation
- Long storage possible before use
- Ability to withstand extreme temperature

Key features

- Low self-discharge rate (less than 3% after 1 year of storage at + 20°C)
- · Hermetic glass-to-metal sealing
- Built-in safety vent (at the negative end of the cell)
- Restricted for transport (class 9)
- Meets shock, vibration and other environmental requirements of military specifications
- Made in UK

Main applications


- Radiocommunications and other military applications
- Beacons and Emergency Location Transmitters
- Sonobuoys
- Life jacket lights
- Professional electronics
- Missiles

Cell size refe	rence	R20 - D
Electrical chara	cteristics	
(typical values relat	ive to cells stored for one year or less at + 30°C max.)	
Nominal capacity (at 0.25 A + 20°C 2.0 V cut off. The capacity restored by the cell varies according to current drain, temperature and cut off).		7.75 Ah
Open circuit voltage	e (at +20°C)	3.0 V
Nominal voltage	(at 0.5 A + 20°C)	2.8 V
Maximum recommo (to avoid over-heati	ended continuous current ing)	2.5 A
the temperature ar	pically up to 5 A. gs may vary according to the pulse characteristics, nd the cell's previous history. Fitting the cell with a ecommended in severe conditions. Consult Saft)	
Storage	(recommended) (possible without leakage)	+30°C (+86°F) max +85°C (+185°F) max
Operating temperature range (Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)		-60°C/+70°C (-76°F/+158°F)
Physical charac	teristics	
Diameter (max)		34.5 mm (1.36 in)
Height (max)		59.8 mm (2.35 in)
Typical weight		85 g (3 oz)
Li metal content		2.4 g
Standard cell come Finish with tabs ava	es with protruding positive end-cap. silable on request.	



G 26





Overall dimensions in mm

Handling precautions


- · Cell is pressurised.
- Do not puncture, open or mutilate.
- Do not obstruct the safety vent mechanism.
- Do not short circuit or charge.
- Do not expose to fire or temperatures above +70°C (+158°F).

Saft Specialty Battery Group


12, rue Sadi Carnot 93170 Bagnolet - France Tel +33 (0)1 49 93 19 18 Fax +33 (0)1 49 93 19 69

River Drive, South Shields
Tyne and Wear, NE33 2TR - UK
Tel +44 (0)191 456 1451
Fax +44 (0)191 456 6383


www.saftbatteries.com



Voltage at mid-discharge versus Current and Temperature (2.0 V cut-off)



Typical discharge profiles at +20°C



Capacity versus Current and Temperature (continuous discharges 2.0 V cut-off)

Doc. N° 31058-2-1005

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft.

For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2.

Published by the Communications Department.

Photo credit: Saft.

Société anonyme au capital de 31 944 000 €

RCS Bobigny B 383 703 873 Produced by Arthur Associates.

