

Document Name	Document No.	Ver	Date	Page
LP8867220F Specification	ZJQM-RD-SPC-A0125	0.0	2015-9-10	1/6

# **EEMB CO., LTD**

# Lithium Iron Phosphate Battery Specification

**Model:** LP8867220F

Capacity: 10Ah

Prepared	Checked	Approved

#### Customer:

<b>Customer Approval</b>	(Customer confirmation)	:
Signature	Checked	Approved

Address: Room ABCD,25/F, Block A, Fortune Plaza, NO.7060 Shennan Road Shenzhen, China

Postal code: 518040

Phone: 0086-755-83022275 FAX: 0086-755-83021966

http://www.eemb.com



<b>Document Name</b>	Document No.	Ver	Date	Page
LP8867220F	ZJQM-RD-SPC-A0125	0.0	2015-9-10	2/6
Specification	20 211 122 21 3 110125	0.0		_, 0

# Catalog

Chapter	Content
0	Catalog
1	Scope
2	Battery Cell Basic Characteristics.
2.1	Model
2.2	Capacity
2.3	Nominal Voltage.
2.4	Weight.
2.5	Internal Impedance
2.6	Dimension.
2.7	Charge.
2.8	Discharge
2.9	Operation Temperature.
2.10	Storage Temperature.
2.11	Storage Relative Humidity
3	Battery Cell Shape and Dimensions.
4	Appearance
5	Battery Cell Specification.
5.1	Electrical Characteristics.
5.1.1	1C <sub>5</sub> A rate discharge capacity.
5.1.2	High temp. discharge capacity.
5.1.3	Low temp. discharge capacity.
5.1.4	Cycle Life
5.1.5	Capacity Retention.
5.2	Acclimatization Characteristics.
5.2.1	High Temp. and High Humidity
5.2.2	Vibration
5.2.3	Drop.
5.2.4	Low-pressure.
5.3	Safety Characteristics.
5.3.1	Overcharge
5.3.2	Short-Circuit.
5.3.3	Heating
5.3.4	Temperature cycle
6	Battery Shipment voltage.
7	Warranty
8	Matters needing attention



Document Name	Document No.	Ver	Date	Page
LP8867220F	ZJQM-RD-SPC-A0125	0.0	2015-9-10	3/6
Specification				

# 1. Scope


This product specification defines the requirements of the rechargeable lithium iron phosphate battery supplied to the customer by EEMB Co., Ltd.

# 2. Battery Cell Basic Characteristics

No.	Item		Characteristics		Remark
2.1	Model		LP8867220F		
2.2	Congoity	Nominal Capacity	10000	mAh	$0.2C_5A$
2,2	Capacity	Minimum	9500	mAh	$0.2C_5A$
2.3	Nom	inal Voltage	3.2	V	
2.4		Weight	Approx.250	g	
2.5	Intern	al Impedance	≤ 15	$m\Omega$	AC 1KHz(50% charge)
		Length	≤ 224	mm	
2.6	Dimension	Width	≤ 67.5	mm	
		Thickness	≤ 9.3	mm	
	Charge	Maximum Current	10000	mA	1.0C <sub>5</sub> A (CC&CV)
2.7		Limited Voltage	3.650±0.020	V	
		End-of Current	250	mA	
2.8	Disahamaa	Maximum Current	20000	mA	2.0C <sub>5</sub> A
2.0	Discharge	End Voltage	2. 0±0.005	V	
2.9	Operation	Charge	0 ~ 45	$^{\circ}\!\mathbb{C}$	
2.9	Temperature	Discharge	<b>-</b> 10 ∼ +60	$^{\circ}\!\mathbb{C}$	
	C4 - m - m	1 month	<b>-</b> 20 ∼ +60	$^{\circ}\!\mathbb{C}$	
2.10	Storage Temperature	3 month	<b>-</b> 20 ∼ +45	$^{\circ}\!\mathbb{C}$	
	Temperature	12 month	<b>-</b> 20 ∼ <b>+</b> 25	$^{\circ}\!\mathbb{C}$	
2.11	Storage R	elative Humidity	65±20	%	

# 3. Shape and Dimensions (Unit: mm)

Item	Specification	
Т	Max9.3	
W	Max67.5	
L	Max224	
L1	Max226	
L2	10±1	
M	36±1	
N	20±0.5	





Document Name	Document No.	Ver	Date	Page
LP8867220F Specification	ZJQM-RD-SPC-A0125	0.0	2015-9-10	4/6

# 4. Appearance

It shall be free from any defects such as remarkable scratches, breaks, cracks, discoloration, leakage, or middle deformation.

#### 5. Specification

# **5.1 Electrical Characteristics**

No.	Item	Criteria	<b>Test Instructions</b>
5.1.1	1C <sub>5</sub> A rate discharge capacity	Discharge Capacity≥ Minimum Capacity	Full charge at $20\pm5$ °C, rest for 30 min, then discharge at the same temperature with $1.0C_5A$ to $2.0V$ .
5.1.2	High temp. discharge capacity	Discharge Time≥54min	Full charge at $20\pm5^{\circ}$ C, store at $55\pm2^{\circ}$ C for 2h, then discharge at the same temperature with $1.0C_5A$ to $2.0V$ .
5.1.3	Low temp. discharge capacity	Discharge Time≥3h	Full charge at $20\pm5$ °C, store at $-10$ °C $\pm2$ °C for $16h\sim24h$ , then discharge at the same temperature with $0.2C_5A$ to $2.0V$
5.1.4	Cycle Life	≥2000 Cycles	After full charge, rest for 10 min, then discharge at 0.5C constant current to 2.0V, rest for 10 minutes. Repeat above steps two times, the battery will be terminated when discharge time less than 84 mins
5.1.5	Capacity Retention	Discharge Time≥4.5 h	After full charge, store at 20±5°C for 28 days. Then discharge with 0.2C <sub>5</sub> A to 2.0V

#### **5.2 Acclimatization Characteristics**

No.	Item	Criteria	Test Instructions
5.2.1	High Temp. and High Humidity	no fire or explosion;	After full charge, store at $40^{\circ}\text{C} \pm 2^{\circ}\text{C}(90\% \sim 95\%\text{RH})$ for 48h. After test, place at $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ for 2h and then discharge with $1\text{C}_5\text{A}$ to end-voltage
5.2.2	Vibration	No deformation, leakage, no fire or explosion; Battery Voltage≥3.2V	Batteries are vibrated 30 min in three mutually perpendicular directions with amplitude of 0.38mm (10~30Hz) or 0.19mm (30~55Hz) and the scanning rate of loct per min
5.2.3	Drop	INo leakage no tire or	Batteries are dropped onto a hard board with the thickness of $18\sim20$ mm from at least 1meter height. Drop the batteries from six different directions and discharge them at $1C_5A$ to end-voltage.
5.2.4	Low-pressure	No leakage, no fire or explosion	Put the batteries in a sealed vacuum and reduce internal pressure gradually to lower than 11.6 kpa. Keep for 6h



Document Name	Document No.	Ver	Date	Page
LP8867220F Specification	ZJQM-RD-SPC-A0125	0.0	2015-9-10	5/6

#### **5.3 Safety Characteristics**

No.	Item	Criteria	Test Instructions		
5.3.1		No fire or evalorion	Put the batteries with thermocouple into the ventilation cabinet. Connect		
	Overcharge		the polarities to constant voltage and adjust the current to 3 C <sub>5</sub> A, voltage to		
			4.8V. Charged the cells at 3C <sub>5</sub> A current 20±5°C with a voltage limit of 4.8V		
			and Current approach 0 A.		
5.3.2		No fire or	Put the batteries with thermocouple into the ventilation cabinet. Batteries		
	Short-Circui	explosion;	are short-circuited by connecting the positive and negative terminals for 11		
	t	The maximum	with a resistance load of $100m\Omega$ . Watch the changes of temperature. Test		
		Temperature: 150°C	the temperature of the batteries until it drops to 10°C.		
5.3.3	Haating	No fire or explosion	Cell is heated in a circulating air oven at a rate of (5±2)°C per minute to		
	Heating		130±2 $^{\circ}$ C, and then placed for 30 minutes at 130±2 $^{\circ}$ C		
5.3.4			After full charge, place the battery in the temperature control box of		
	20±5°C, do the following st		$20\pm5$ °C, do the following steps:		
	Temperature	No leakage, no fire	(1)Put the battery into test chamber of 75°C±2°C and keep for 6h.		
	cycle	or explosion	2)Lower the temperature to -40±2°C and keep for 6h		
			(3)Temperature conversion time is no longer than 30 min		
			(4)Repeat the above three steps for 10 cycles.		

Note: Unless otherwise specified, all tests stated in this specification are conducted at the following conditions: Temp. :  $20\pm5^{\circ}$ °C; Relative Humidity:  $25\%\sim85\%$ .

#### 6. Battery shipment voltage: 3.2~3.4V

#### 7. Warranty

One year warranty after the date of production

#### 8. Matters needing attention

Strictly observes the following needing attention. EEMB will not be responsible for any accident occurred by handling outside of the precautions in this specification.

# ! Danger

- Strictly prohibits heat or throw cell into fire.
- Strictly prohibits throw and wet cell in liquid such as water, gasoline or drink etc.
- Strictly prohibits use leave cell close to fire or inside of a car where temperature may be above 60°C. Also do not charge / discharge in such conditions.
- Strictly prohibits put batteries in your pockets or a bag together with metal objects such as necklaces. Hairpins, coins, or screws. Do not store or transportation batteries with such objects.
- Strictly prohibits short circuit the (+) and (-) terminals with other metals.
- Do not place Cell in a device with the (+) and (-) in the wrong way around.
- Strictly prohibits pierce Cell with a sharp object such as a needle.
- Strictly prohibits disassemble or modify the cell.
- Strictly prohibits welding a cell directly.
- Do not use a Cell with serious scar or deformation.
- Thoroughly read the user's manual before use, inaccurate handling of lithium ion rechargeable cell may cause leakage, heat, smoke, an explosion, or fire, capacity decreasing.



Document Name	Document No.	Ver	Date	Page
LP8867220F Specification	ZJQM-RD-SPC-A0125	0.0	2015-9-10	6/6

# ! Warning

- Strictly prohibits put cell into a microware oven, dryer, or high-pressure container.
- Strictly prohibits use cell with dry cells and other primary batteries, or new and old battery or batteries of a different package, type, or brand.
- Stop charging the Cell if charging is not completed within the specified time.
- Stop using the Cell if abnormal heat, odor, discoloration, deformation or abnormal condition is detected during use, charge, or storage.
- Keep away from fire immediately when leakage or foul odor is detected.
- If liquid leaks onto your skin or clothes, wash well with fresh water immediately.
- If liquid leaking from the Cell gets into your eyes, do not rub your eyes. Wash them well with clean edible oil and go to see a doctor immediately.

#### ! Caution

- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Charging with specific charger according to product specification. Charge with CC/CV method.
   Strictly prohibits revered charging. Connect cell reverse will not charge the cell. At the same time, it
   will reduce the charge-discharge characteristics and safety characteristics; this will lead to product heat
   and leakage.
- Store batteries out of reach of children so that they are not accidentally swallowed.
- If younger children use the Cell, their guardians should explain the proper handling.
- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Batteries have life cycles. If the time that the Cell powers equipment becomes much shorter than usual, the Cell life is at an end. Replace the Cell with a new same one.
- When not using Cell for an extended period, remove it from the equipment and store in a place with low humidity and low temperature.
- While the Cell pack is charged, used and stored, keep it away from objects or materials with static electric charges.
- If the terminals of the Cell become dirty, wipe with a dry clothe before using the Cell.
- Storage the cell in storage temperature range as the specifications. After full discharged, we suggest that charging to 3.2~3.4V with no using for a long time.
- Do not exceed these ranges of the following temperature ranges:

Charge temperature range :  $0^{\circ}$ C to  $45^{\circ}$ C;

Discharge temperature range :  $-10^{\circ}$ C to  $60^{\circ}$ C.

Store less than 1 month :  $-20^{\circ}\text{C} - +60^{\circ}\text{C}$ Store less than 3 months :  $-20^{\circ}\text{C} - +45^{\circ}\text{C}$ Store less than 1 year :  $-20^{\circ}\text{C} - +25^{\circ}\text{C}$ 

# ! Special Notice

Keep the cell in 50% charged state during long period storage. We recommend to charge the battery up to 50% of the total capacity every 3 months after receipt of the battery and maintain the voltage 3.2~3.4V. And store the battery in cool and dry place.

EEMB reserves the final explanation. Please use battery strictly according to specification. EEMB will not be responsible for any inappropriate operation. EEMB keeps the right to change product specifications without previous notice. If any question, please consult with the manufacturer