

TAIYO PSR-4000BN Series

LIQUID PHOTOIMAGEABLE SOLDER MASK

- ③ **Screen or Spray Application**
- ③ **Available in Green or Dark Green**
Semi-Gloss Finish
- ③ **RoHS Compliant**
- ③ **High Viscosity version for improved**
edge coverage on High Traces
- ③ **Compatible with Lead-Free Processing**
- ③ **Best In Class for Small Hole Clearing**
- ③ **Wide Processing Window**
- ③ **Fine Dam Resolution**
- ③ **Withstands ENIG & Immersion Tin**

Revised March 2005



TAIYO AMERICA, INC.®

2675 Antler Drive, Carson City, NV 89701 • (775) 885-9959 • Fax: (775) 885-9972 • www.taiyo-america.com

Technical Data Sheet

www.DataSheet4U.com

PROCESSING PARAMETERS FOR PSR-4000BN SERIES

PSR-4000BN Series includes **PSR-4000BN**, **PSR-4000BN (HV)**, and **PSR-4000BN (DG)**. They are two-component, alkaline developable LPI solder mask products for flood screen and spray application methods. The products are designed to be user friendly with wide processing latitudes, low odor, fast developing and good resistance to alternate metal finishes such as ENIG and immersion Tin while maintaining dams of 3 mils or less. The **PSR-4000 BN (HV)** provides improved edge coverage over high circuits while the **PSR-4000BN (DG)** provides the same benefit in a Dark Green color. **PSR-4000BN Series** meets or exceeds the requirements of IPC SM-840C Class H and Class T, Bellcore GR-78-CORE Issue 1, and has a UL flammability rating of 94V-0. All Taiyo America products comply with the Directive 2002/95/EC of the European Parliament and of the Council of 27 January 2003 on the Restriction of the use of certain Hazardous Substances (RoHS) in electrical and electronic equipment.

PSR-4000BN SERIES COMPONENTS

	PSR-4000BN Series/ CA-40BN		
	BN	HV	DG
Mixing Ratio	100 parts	43 parts	
Color	Green	White	
Mixed Properties	BN	HV	DG
Solids	77%	77%	77%
Viscosity	135-165ps	175-225ps	175-225ps
Specific Gravity	1.39	1.39	1.39

MIXING

PSR-4000BN Series is supplied in pre-measured containers with a mix ratio by weight of 100 parts **PSR-4000BN** and 43 parts **CA-40BN**. **PSR-4000BN** can be mixed by hand with a mixing spatula for 10 – 15 minutes. Mixing can be done with a mechanical mixer at low speeds to minimize shear thinning for 10 – 15 minutes. Also, mixing can be done with a paint shaker for 10 – 15 minutes.

PRE-CLEANING

Prior to solder mask application, the printed circuit board surface needs to be cleaned. Various cleaning methods include Pumice, Aluminum Oxide, Mechanical Brush, and Chemical Clean. All of these methods will provide a clean surface for the application of **PSR-4000BN Series**. Hold time after cleaning the printed circuit board should be held to a minimum to reduce the oxidation of the copper surfaces.



TAIYO AMERICA, INC.[®]

2675 Antler Drive, Carson City, NV 89701 • (775) 885-9959 • Fax: (775) 885-9972 • www.taiyo-america.com

Technical Data Sheet

www.DataSheet4U.com

PROCESSING PARAMETERS FOR PSR-4000BN SERIES

SCREEN PRINTING Method: Single Sided and Double Sided Screening

- Screen Mesh: 74 – 110
- Screen Mesh Angle: 22.5° Bias
- Screen Tension: 20 - 28 Newtons
- Squeegee: 60 – 80 durometer
- Squeegee Angle: 27 – 35°
- Printing Mode: Flood / Print / Print
- Flood Pressure: 20 – 30 psi
- Printing Speed: 2.0 – 9.9 inches/sec
- Printing Pressure: 60 – 100 psi

TACK DRY CYCLE

The Tack Dry step is required to remove solvent from the solder mask film and produce a firm dry surface. The optimum dwell time and oven temperature will depend on oven type, oven loading, air circulation, exhaust rate, and ramp times. Excessive tack dry times and temperature will result in difficulty developing solder mask from through holes and a reduction in photo speed. Insufficient tack dry will result in artwork marking and/or sticking. Typical tack dry conditions for **PSR-4000BN Series** are as followed:

- Oven Temperature: 150 - 185°F (65 - 85°C)
- For Single-Sided (Batch Oven)
 - 1st Side: Dwell Time: 10 - 20 minutes
 - 2nd Side: Dwell Time: 25 - 45 minutes
- For Double-Sided (Conveyorized or Batch Oven)
- Dwell Time: 25 - 60 minutes

EXPOSURE

PSR-4000BN Series requires UV exposure to define solder mask dams and features. The spectral sensitivity of **PSR-4000BN Series** is in the area of 365 nm. Exposure times will vary by bulb type and age of the bulb. Below are guidelines for exposing **PSR-4000BN Series**.

- Exposure Unit: 5 kW or higher
- Stouffer Step 21: Clear 8 minimum (on metal / under phototool)
- Energy: 250 mJ / cm² minimum (under phototool)



TAIYO AMERICA, INC.[®]

2675 Antler Drive, Carson City, NV 89701 • (775) 885-9959 • Fax: (775) 885-9972 • www.taiyo-america.com

Technical Data Sheet

www.DataSheet4U.com

PROCESSING PARAMETERS FOR PSR-4000BN SERIES

DEVELOPMENT

PSR-4000BN Series is developed in an aqueous sodium or potassium carbonate solution. Developing can be done in either a horizontal or vertical machine.

- Solution: 1% by wt. Sodium Carbonate or 1.2% Potassium Carbonate
 - pH: 10.6 or greater
 - Temperature: 85 - 105°F (29 - 41°C)
 - Spray Pressure: 25 - 45 psi
 - Dwell Time in developing chamber: 45 - 90 seconds
 - Water rinse is needed to remove developer solution followed by a drying step
-

FINAL CURE **PSR-4000BN** needs to be thermally cured to insure optimal final property performance. Thermal curing can be done in a batch oven or conveyORIZED oven.

- Temperature: 275 – 300°F (135 – 149°C)
 - Time at Temperature: 45 – 60 minutes
-

For Process Optimization please contact your local Taiyo America Representative



TAIYO AMERICA, INC.®

2675 Antler Drive, Carson City, NV 89701 • (775) 885-9959 • Fax: (775) 885-9972 • www.taiyo-america.com

Technical Data Sheet

www.DataSheet4U.com

FINAL PROPERTIES FOR PSR-4000BN

IPC-SM-840C, Class H & T, Solder Mask Vendor Testing Requirements

TEST	SM-840 PARAGRAPH	REQUIREMENT	RESULT
Visual	3.4.8	Uniform in Appearance	Pass
Curing	3.4.5	Ref: 3.6.1.1, 3.7.1 and 3.7.2	Pass
Non-Nutrient	3.4.6	Does not contribute to biological growth	Pass
Dimensional	3.4.10	No Solder Pickup and Withstand 500 VDC	Pass
Pencil Hardness	3.5.1	Minimum "F"	Pass – 8H
Adhesion	3.5.2	Rigid – Cu, Ni, FR-4	Pass
Machinability	3.5.3	No Cracking or Tearing	Pass
Resistance to Solvents and Cleaning Agents	3.6.1.1	Table 3 Solvents	Pass
Hydrolytic Stability and Aging	3.6.2	No Change after 28 days of 95-99°C and 90-98% RH	Pass
Solderability	3.7.1	No Adverse Effect J-STD-003	Pass
Resistance to Solder	3.7.2	No Solder Sticking	Pass
Dielectric Strength	3.8.1	500 VDC / mil Minimum	2800 VDC/mil
Thermal Shock	3.9.3	No Blistering, Cracking or De-lamination	Pass

Specific Class "H" Requirements

TEST	SM-840 PARAGRAPH	REQUIREMENT	RESULT
Flammability	3.6.3	UL 94V-0	Pass – File #E166421 UL Name: PSR-4000BN / CA-40BN PSR-4000BN (HV) / CA-40BN PSR-4000BN (DG) / CA-40BN
Insulation Resistance Before Soldering After Soldering	3.8.2	5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum	Pass (1.29 x 10 ¹³ ohms) Pass (3.31 x 10 ¹³ ohms)
Moisture & Insulation Resistance Before Soldering–In Chamber Before Soldering–Out of Chamber After Soldering–In Chamber After Soldering–Out of Chamber	3.9.1	5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum	Pass (6.61 x 10 ¹⁰ ohms) Pass (2.50 x 10 ¹² ohms) Pass (1.89 x 10 ¹⁰ ohms) Pass (1.07 x 10 ¹³ ohms)
Electrochemical Migration	3.9.2	>2.0 x 10 ⁶ ohms, no dendritic growth	Pass (1.35 x 10 ¹² ohms)

Specific Class "T" Requirements

TEST	SM-840 PARAGRAPH	REQUIREMENT	RESULT
Flammability	3.6.3	Bellcore O ₂ Index – 28 minimum	Pass – 74
Insulation Resistance Before Soldering After Soldering	3.8.2	5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum	Pass (2.23 x 10 ⁹ ohms) Pass (1.14 x 10 ¹³ ohms)


TAIYO AMERICA, INC.®

2675 Antler Drive, Carson City, NV 89701 • (775) 885-9959 • Fax: (775) 885-9972 • www.taiyo-america.com

Technical Data Sheet

www.DataSheet4U.com

FINAL PROPERTIES FOR PSR-4000BN

Specific Class "T" Requirements

TEST	SM-840 PARAGRAPH	REQUIREMENT	RESULT
Moisture & Insulation Resistance Before Soldering-In Chamber Before Soldering-Out of Chamber After Soldering-In Chamber After Soldering-Out of Chamber	3.9.1	5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum 5 x 10 ⁸ ohms minimum	Pass (1.77 x 10 ⁹ ohms) Pass (1.80 x 10 ¹³ ohms) Pass (2.78 x 10 ¹⁰ ohms) Pass (2.31 x 10 ¹³ ohms)
Electrochemical Migration	3.9.2	< 1 decade drop, no dendritic growth	Pass

Additional Tests / Results

TEST	REQUIREMENT	RESULT
Dielectric Constant	Internal Test at 1 MHz	4.5
Dissipation Factor	Internal Test at 1 MHz	0.0290
CTE	Internal Test (α_1/α_2)	70 / 140 ppm
Outgassing Test ASTM E-595-90 A 2 J/cm ² UV Cure was done after thermal cure.	TML ≤ 1% CVCM ≤ 0.10%	TML-0.51% CVCM-0.02%
Electroless Nickel / Immersion Gold Resistance	Nickel(85C/30 min)Tape Test Adhesion	Pass
Solvent Resistance	Acetone: MEK: IPA: PMA:	No attack – 24 hours Pass No attack – 24 hours Pass No attack – 24 hours Pass No attack – 24 hours Pass
Acid Resistance	HCl – 10%: H ₂ SO ₄ – 10%:	No attack – 30 Minutes Pass No attack – 30 Minutes Pass
Base Resistance	NaOH – 10%: Boiling Water Resistance:	No attack – 30 Minutes Pass No attack – 15 Minutes Pass
Solder / Flux Resistance (Alphametals)		
Alpha 857 water soluble:	No attack – 1 x 10 sec float (260C)	Pass
NR060 no-clean:	No attack – 1 x 10 sec float (260C)	Pass
3355-NB rosin-based:	No attack – 1 x 10 sec float (260C)	Pass
NR-3000A4 no-clean:	No attack – 1 x 10 sec float (260C)	Pass
Solder/Flux Resistance(Multicore) X32-10M no-clean:	No attack – 1 x 10 sec float (260C)	Pass
X32-06I no-clean:	No attack – 1 x 10 sec float (260C)	Pass
Solder/Flux Resistance-(Sanwa) SR-270 rosin-based:	No attack – 1 x 10 sec float (260C)	Pass
Conformal Coating Adhesion: Humiseal 1 B31 acrylic: Humiseal 1A20 urethane: Dow Corning 3-1753 silicone:	Crosscut (10/10) after tape Crosscut (10/10) after tape Crosscut (10/10) after tape	100/100 100/100 100/100
Glue Dot Adhesion – Loctite 3609	Adhesion of Glue Dot to PSR-4000BN	Excellent

Taiyo America, Inc. (TAIYO) warrants its products to be free from defects in materials and workmanship for the specified warranty period (**PSR-4000BN / CA-40BN Warranty period is 12 Months**) provided the customer has, at all times, stored the ink at a temperature of 68°F or less. TAIYO accepts no responsibility or liability for damages, whether direct, indirect, or consequential, resulting from failure in the performance of its products. If a TAIYO product is found to be defective in material or workmanship, its liability is limited to the purchase price of the product found to be defective. TAIYO MAKES NO OTHER WARRANTY, EXPRESS OR IMPLIED, AND MAKES NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR ANY PARTICULAR PURPOSE. TAIYO'S obligation under this warranty shall not include any transportation charges or costs of installation or any liability for direct, indirect, or consequential damages or delay. If requested by TAIYO, products for which a warranty claim is made are to be returned transportation prepaid to TAIYO'S factory. Any improper use or any alteration of TAIYO'S product by the customer, as in TAIYO'S judgment affects the product materially and adversely, shall void this limited warranty.


TAIYO AMERICA, INC.®

2675 Antler Drive, Carson City, NV 89701 • (775) 885-9959 • Fax: (775) 885-9972 • www.taiyo-america.com